



# **LUCAS** *Coatings & Mastics for the Roofing Trade*

R. M. Lucas Co. 3211 S. Wood St. Chicago, IL 60608 (773) 523-4300 [rmlucas.com](http://rmlucas.com)

## **PRODUCT DATA BULLETIN**

### **#748 ALUMINUM ROOF COATING - 3 Lb. FIBRATED**

#### **PURPOSE**

#748 3 Lb. Aluminum Roof Coating is designed to provide a reflective surface for roofs, metal buildings, and mobile homes. Aluminum pigmented asphalt coatings can substantially reduce interior building temperature and prolong roof service life. #748 is a heavy bodied longer lasting coating that will outlast thinner non-fibered aluminum coatings.

#### **PRODUCT DESCRIPTION**

Lucas #748 3 Lb. Aluminum Roof Coating is formulated from specially refined asphalt, aliphatic solvents, reinforcing non-asbestos fibers and 3 lbs. per gallon of ASTM D-962 leafing aluminum paste. Formulated to spread easily and evenly by brush or spray.

#### **APPLICATION**

Surface to be coated must be dry and free of dirt or corrosion particles. Stir coating thoroughly and continuously before and during application. Power mixing is recommended. Apply evenly with a soft bristle brush, roller or suitable spray equipment at the rate of not less than one and not more than one and one-half gallons per 100 square feet. For best results, brush coating in one direction with the slope of the roof. Do not apply over fresh roof repairs or coating. Roofing asphalts should be allowed to cure thoroughly to avoid alligating and staining. As this condition is unpredictable, we recommend that the user apply a small amount of #748 to the area of the roof to be coated in order to test its performance. Use #748 as it comes from the container, no thinning is necessary with this product. Clean up Lucas #125 Safe Solve.

#### **CAUTION**

Combustible mixture; keep away from heat and open flames. Avoid prolonged contact with skin or fumes. If irritation occurs seek medical attention. Do not use near heat or open flame. If swallowed, do not induce vomiting. Keep out of reach of children. Read MSDS prior to use.

California Proposition 65 Warning: This product may contain chemicals known to the State of California to cause cancer, birth defects and/or reproductive harm.

## #748 SPECIFICATION

Applicable Specification	ASTM D-2824 Type III
Viscosity ASTM D-562	625g @ 77°F (25°C) (3,100 cps)
Recommended rate of application	1 to 1 1/2 gal. per 100 sq. ft
% Asphalt	32 min
% Solids	50 min
% Non-volatile	54 max
Weight per gallon	9.1 lbs.
Initial Solar Reflectivity ASTM E-903	71%
Aged Solar Reflectivity ASTM E-1918	54%
Aluminum paste ASTM D-962 ASTM D-962 type 2	3 Lbs. per gallon
Flash point (TCC)	+100°F (38.7°C)
Container sizes	5, 55

Lucas #748 Aluminum Roof Coating meets all requirements of the Urban Heat Islands Provision of the Chicago Energy Code.



TO THE EXTENT ALLOWED BY LOCAL LAW, EXCEPT AS SET FORTH BELOW, SELLER MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE WITH RESPECT TO THE GOODS HEREIN SOLD. THERE ARE NO OTHER WARRANTIES OF ANY KIND EXPRESS OR IMPLIED BEYOND THE TERMS SET FORTH ON THE FACE HEREOF. NO EMPLOYEE OR AGENT OF SELLER IS AUTHORIZED TO ALTER THE TERMS HEREOF.

Seller warrants that this product shall be free of any defect in material or workmanship under normal use for a period of ONE YEAR from the date of purchase. This warranty does not extend to any defect or failure caused by misuse and/or incorrect application. LIMITATION OF LIABILITY: In the event of a defect or failure falling under this warranty, Buyers sole remedy shall be refund of the purchase price or replacement of the defective material, at Seller's option. Under no circumstances shall Seller be liable for any losses or damages caused by this product, whether direct, indirect, special, incidental or consequential damages, whether based on contract, tort (including negligence) or any other legal theory.

NOTE: Some or all of the foregoing may not apply or may be invalid under the laws applicable to Buyer's purchase or claim. Consult local law to determine the applicability of any of the foregoing in the event of any defect or failure of this product.